# **TECHNICAL DATA SHEET**

YIPIN<sup>®</sup> Iron Oxide Pigment Iron Oxide Orange 4960



Edition of	2015-12-04		
Туре	Orange pigment		
Delivery Form	Powder		
Chemical Class	Synthetic iron oxide		
Color Index	Pigment Yellow 42(77492)/ Pigment Red		
	101(77491)		
CAS No.	20344-49-4/1309-37-1		
Use Recommendation	Coating、Construction		

COLOR VALUES AND TINTING STRENGTH						
Reference			Standard			
	<u>Min</u>	<u>Max</u>	Test Method			
Reduction with titanium dioxide (1:5)	R-706		Similar to ASTM D-387			
△ <b>L*</b>	-0.7	+0.7				
<b>△a*</b>	-0.7	+0.7				
$\triangle$ b*	-0.7	+0.7				
△E*ab		1.0				
Binder	R-05					
Relative tinting strength [%]	98.0	103.0	Similar to ASTM D-387			

TECHNICAL DATA			
	<u>Min</u>	<u>Max</u>	Test Method
Water-Soluble Content [%]		0.5	ASTM 1208-96
Sieve Residue (0.045mm) [%]		0.05	ASTM D 185
Fe <sub>2</sub> O <sub>3</sub> [%]	86.0		ASTM D 50
PH Value	5.0	7.0	ASTM 1208-96
Moisture (After Production) [%]		1.0	ASTM D 280-01
Loss on Heating 1000°C <sup>1/2</sup> h <b>[%]</b>		12.0	ASTM D1208

YIPIN PIGMENTS, INC.Tel:+1-909-243-7394Fax: +1-909-243-7397www.yipin.com一品颜料Tel:+86-21-5950 8509Fax: +86-21-5950 7893wh@yipin.com

## TECHNICAL DATA SHEET

YIPIN® Iron Oxide Pigment Iron Oxide Orange 4960



#### Approx.

Water Absorption [g/100g]	~40	ASTM D 28	
STANDARD PACKAGING	50lb/bag		

### TRANSPORT AND STORAGE

Protect against weathering. Store in a dry place and avoid extreme fluctuations in temperature. Special conditions for opened packaging: Close bags after use to prevent the absorption of moisture and contamination.

#### **SAFETY**

The product is not classified as dangerous under the relevant EC directives and corresponding national regulations valid in the individual EU member states. It is not dangerous according to transport regulations. In countries outside the EU, compliance with the respective national legislation concerning the classification, packaging, labeling and transport of dangerous substances must be ensured.

The information contained in the safety data sheet should be observed.

This contains information on handing, product safety and ecology.

is given in good faith, without warranty. It is also applies proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General conditions of sale and delivery.

2 of 2 12/4/2015 Copyright Shanghai Yipin Pigments Co., Ltd