

## **QUAKER COLOR**

### DIVISION OF McADOO & ALLEN, INC.

201 S. HELLERTOWN AVENUE P.O. BOX 219 QUAKERTOWN, PENNSYLVANIA 18951-0219 (215) 536-3520 FAX (215) 536-6464 www.quakercolor.com

### **Technical Data Sheet**

Product Code: AB-72FD

#### DESCRIPTION

AB-72FD is NMP free, high performance aliphatic polyester urethane dispersion with adhesion over plastic and metal substrates. It could be used as a one component or crosslinked with isocyanate and through COOH functional groups to form high chemical and UV resistant coatings.

#### **APPLICATIONS**

- Interior and exterior automotive plastics
- Consumer electronics such as cellular phones, computers and TV housing
- Aircraft hangars flooring
- Other applications requiring high chemical and UV resistance

#### **FEATURES**

- Adhesion to Aluminum, CRS, Tin, PC
- Excellent chemical resistance, including hydraulic fluids
- Excellent water resistance
- Excellent hot hardness

#### **PROPERTIES**

Clear Liquid
31 +/- 2
8.0
1.04
8.6
73

#### **STORAGE**

Store in a cool, dry place, preferably less than 80°F, to ensure a useful shelf life of 18 months. Protect from freezing. Mix before use.



# QUAKER COLOR

## DIVISION OF McADOO & ALLEN, INC.

201 S. HELLERTOWN AVENUE P.O. BOX 219 QUAKERTOWN, PENNSYLVANIA 18951-0219 (215) 536-3520 FAX (215) 536-6464 www.quakercolor.com

### STARTING POINT FORMULATION

Material Component 1	Lbs.	Supplier
AB-72FD	100.00	Quaker Color
TEGO 901W	0.50	Degussa
BYK347	0.50	BYK-Chemie
TS-100	3.00	Degussa
Rheolate 300	1.00	Aqualon
OTL-Blue-50	20.00	Quaker Color
Crosslinker		
Rhodocoat WAT4	5%	Rhodia

## TEST RESULTS

Clear Films, no crosslinker, 7 days ambient cure

Hardness	Sward	34			Pencil		4H					
Dry Adhesion, tape	Al	5	CRS	5	B1000	5	Tin	4	PC	5		
Mechanical Properties	Tensile	7455		Elongation	392		Modulus 5166		6			
MEK Resistance	DR to Soften	50 DR to Mar		38		DR to Remove	165					
IPA Resistance	DR to Soften		200+		DR to Mar	18		DR to Remove	Not Applicable			
Hydraulic Fluid	7 hrs spot		Skydrol, LD4	'	No effect	HYJE	HYJET Slight softening, red		YJET Slight softening, reco		ng, recove	ers



## **QUAKER COLOR**

## DIVISION OF McADOO & ALLEN, INC.

201 S. HELLERTOWN AVENUE P.O. BOX 219 QUAKERTOWN, PENNSYLVANIA 18951-0219 (215) 536-3520 FAX (215) 536-6464 www.quakercolor.com

Pigmented Films: 30 min at 76°C and 3 days ambient cure, 5% Isocyanate Crosslinker

DFT 1.5 mils	AATCC/ISO 105	5 Finger Scratch test
PC Substrate	Grey Scale	2N 5N 8N 13N
Dry Cloth	5	-
Windex x 10 DR	4-5	-
Fantastic x 10 DR	4-5	-
Formula 409 x 10DR	4-5	-
Suntan @74°C x 1hr		5, pass 13N
DEET @74°C x 1hr		3-4, pass 5N

Quaker Color manufactures all its products under carefully controlled conditions to meet rigid specifications. The values given in this publication are typical values intended as guidelines for the use of the products, they are not specifications. It is the user's responsibility to thoroughly test the product in their particular application to determine its performance, efficacy and safety. Should you require the actual specifications currently enforced on specific products contact your Quaker Color representative for the appropriate information.