

ADDITOL[®] VXL 6212

TYPE

Cationic, highly molecular resinlike wetting agent for inorganic and organic pigments

FORM OF DELIVERY (f.o.d.)

Active substance

approx. 30 %

Appearance

medium-viscous liquid

PRODUCT DATA

Determined per batch:

Dynamic Viscosity DIN EN ISO 3219 dynamic viscosity (25 1/s; 23 °C)	[mPa.s]	100 - 300
---------------------------------------------------------------------------	---------	-----------

Non-Volatile Matter DIN 55671 non-volatile matter (150 °C; 10 min)	[%]	29 - 31
--------------------------------------------------------------------------	-----	---------

Not continually determined:

Colour / Appearance VLN 250 colour		brown
---------------------------------------	--	-------

Density (Liquids) DIN EN ISO 2811-2 density approx. (20 °C)	[g/cm ³]	1,07
----------------------------------------------------------------------	----------------------	------

Flash Point DIN EN ISO 1523 flash point approx.	[°C]	59
-------------------------------------------------------	------	----

SPECIAL PROPERTIES

Improves the wetting of also very difficult dispersable pigments in solvent-containing high-grade automotive series, car repair and industrial paints based on acrylates.

Shortens the dispersing time.

Prevents the reflocculation of the pigments.

Improves gloss and levelling.

SUGGESTED USES

Additol VXL 6212 permits a higher pigmentation of the mill base without interfering viscosity increase and shortens the dispersing time. The ready pigment pastes and paints are distinguished by a high colloidal stability and do not tend to a reflocculation of the pigments.

By using Additol VXL 6212, in solvent-containing acrylate systems, a stabilizing effect on the binder can be observed.

The reactivity in baking paints and polyisocyanate cross-linking acrylic systems is not negatively affected by addition of Additol VXL 6212.

PROCESSING

Additol VXL 6212 must be ground jointly with the pigments.

The recommended quantity to be added, calculated on pigment, is as follows:
for inorganic pigments: 3.0 - 10.0 %
for organic pigment: 10.0 - 50.0 %.

We recommend determining the optimum quantity of Additol VXL 6212 for each pigment or each pigment blend.

Possible foam formation in the mill base may be prevented by an addition of Additol XL 490/50BAC. This additive improves the levelling at the same time.

STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 730 days.

Opened vessels have to be closed immediately.

DISTINGUISHING FEATURES

In comparison to Additol XL 260 Additol VXL 6212 has a much better effectiveness in acrylate systems.

5.0/30.03.2017 (replaces 4.0/17.09.2013)

• Worldwide Contact Info: www.allnex.com •

Disclaimer: allnex Group companies ("allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.
© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.