

AL-223-50

DESCRIPTION

Medium Oil Alkyd Resin diluted in Mineral Spirits

FEATURES

- Good Gloss, Flexibility and Brochability .
- Good Drying ..

APPLICATIONS

- Architectural and Industrial Coating and Primers

TYPICAL PROPERTIES

Variable	Units	Min Value	Max value	Analysis technique
Acid Value, solids	mg KOH/gr sample		12	TARQ-110
Percent solids	%	49	51	TARQ-210
Gardner Color	N/A		6	TARQ-300
Appearance	N/A	Clear	Clear	Visual
Gardner Viscosity @ 77°F	N/A	Z1	Z3	TARQ-310

ADDITIONAL INFORMATION

Variable	Value	
Density (lb./gal) a 77 °F	7.65 (+/- 0.1)	



AL-223-50

RECOMMENDATIONS

- This resin is designed for use in air drying coatings, recommended dryers and its active metal base concentration on resin solids are:

0.07 % Cobalt.

0.18 % Calcium.

0.30 % Zirconium

- For any questions, consult your Reacciones Quimicas sales representative.

STORAGE

Keep containers cool and dry, away from any source of heat, spark and flame.

SAFETY AND HANDLING

The detailed information for the safe handling of Resin AL-223-50 is found in its Safety Data Sheet which is available with your Reacciones Químicas SA de CV sales representative.

Last Revision: May/16/2017

STATEMENT OF DISCLAIMER AND LIMITATION OF LIABILITY

To the best of our knowledge, the information contained in this document is accurate. The products sold hereby will comply with the relevant specifications of Seller at the time of shipment. Seller's specifications are subject to change at any time without notice to Buyer. Buyer must give written notice to Seller of any defect alleged and covered by this warranty, together with details of identification, including product codes, description and date of purchase, within thirty (30) days from Shipment of the product or before the expiration date of the shipping life, whichever occurs first. THE WARRANTY DESCRIBED IN THIS DOCUMENT SHALL REPLACE ANY OTHER EXPRESS OR IMPLIED WARRANTIES, INCLUDING ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, WITHOUT LIMITATION. THERE IS NO WARRANTY EXTENDING BEYOND THE DESCRIPTION INDICATED IN THE TEXT OF THIS DOCUMENT. Buyer's sole and exclusive remedy against Seller shall be the replacement of the product or the refund of the purchase price in the event Seller finds that the product has any defective condition. IN NO EVENT SHALL THE SELLER BE LIABLE FOR ANY INDIRECT, SPECIAL, PUNITIVE. INCIDENTAL OR CONSEQUENTIAL DAMAGES, WHETHER FOR LOSS OF PROFITS, LOSS OF SALES, PERSONAL INJURY OR PROPERTY DAMAGE, OR FOR ANY OTHER CAUSE. The sole purpose of this exclusive remedy is to provide the Buyer with replacement of the product or reimbursement of the purchase price if there is any defect in materials or workmanship in the manufacture of the product. This exclusive remedy shall not be deemed to have ceased to serve its essential purpose provided the Seller is willing to replace the product or reimburse the purchase price and is qualified to do so. The final determination as to the suitability of the material for the contemplated use, the manner of use and if the suggested use violates any patent, is the sole responsibility of the Purchaser.