PROTECTIVE & MARINE COATINGS

Product Application details	CRAYAMID [®] 140 is a low viscosity liquid amino polyamide resin that can be used in the manufacture of solventless epoxy coatings and adhesives. It is also used to cure epoxy resins in casting and laminating applications where excellent mechanical properties and chemical resistance are essential.				
Polymer Type	Amino-polyamide Resin				
Sales Specifications	Solid Content at 125°C, % (ISO 3251)			100	
	Viscosity at 40°C, mPa.s (Brookfield SC4-21/13R, 9s-1) (ISO 3219)			3500 - 5500	
	Colour, Gardner scale (ISO 4630)			11 max	
	Total Amine value, mg KOH/g (CVI 069) Note (I)			370 - 410	
Other Characteristics ¹	Density / Specific Gravity at 20°C, g/ml (ISO 2811)			0.97	
	Typical Active Hydrogen Equivalent weight95				
	Note (I) : CVI 069 uses Perchloric acid.				
	1 The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications				
	RECOMMENDATIONS FOR USE The principal use of CRAYAMID [®] 140 is as a hardener for epoxy resins. The selection of a particular grade of epoxy resin will depend on the end use, but generally speaking, epoxy resins having an epoxide equivalent of approximately 200 (1) are recommended for adhesives and high build solventless coatings. For solvent-based coatings the medium epoxy resins (2) may be used as co-reactants. Whilst the mix ratio when using CRAYAMID [®] polyamides is not critical, optimum performance of a coating is achieved by stoichiometric mixing of the epoxy and CRAYAMID [®] 140. The mix ratio is calculated from the active hydrogen equivalent weight (AHEW) since each epoxy group in the base resin will react with one active hydrogen present in the polyamide. The AHEW of CRAYAMID [®] 140 is typically 95. Considering that each epoxy reacts with one reactive hydrogen, the mix ratio of CRAYAMID [®] 140 and an epoxy resin with epoxide equivalent approx. 200 (1) is calculated as follows:				
Formulation Guidelines	Resin	Mass of solid resin (g)	Mass of resin solution (g)		
	CRAYAMID [®] 140	95	95		
	75% epoxy resin	200	267		
	The resulting epoxy:polyamide mix ratio in this case is approx. 65:35 on solid resin. Excess polyamide in a coating will impart flexibility and adhesion at the expense of solvent resistance. <u>CURE RATE</u> A 70:30 epoxy resin (2):CRAYAMID [®] 140 blend (on solid resin) will reach a tack-free time in 210 minutes at 25°C. Films will obviously dry to the touch more rapidly if higher molecular weight epoxy resins are used. An induction period is recommended to ensure complete compatibility. Cure of epoxy:polyamide systems can be accelerated by a range of catalysts, and in particular Tris(dimethylaminomethyl) phenol types (3) which are recommended for use at a level of 1 - 5% (calculated by weight on total resin). It should be noted, that when catalysts are employed, pot life will be reduced and there may be an adverse effect on flexibility and colour. More rapid cure may also be obtained by heating at elevated temperatures.				



	POT LIFE Since reaction between the epoxy resin and CRAYAMID [®] 140 commences as soon as they are mixed, the system has a limited pot life. This is affected by a number of factors, such as temperature, mass of material and solids content, increases of which will reduce pot life. Solvent balance and use of accelerators will also influence the period for which a mix is usable. Solvents have a considerable effect on pot life, with alcohols tending to reduce pot life and esters and ketones tending to extend it. Since the ketones and esters form complexes with amino polyamides on storage, these solvents should only be incorporated into the epoxy resin component. The pot-life of a CRAYAMID [®] 140:epoxy resin system is dependent upon various factors including cure temperature, reactant ratio, accelerators, and fillers. CRAYAMID [®] 140:epoxy resin adhesives will cure at ambient temperature but cure time can be reduced by heating to elevated temperature.		
	<u>ADHESION</u> CRAYAMID [®] 140:epoxy resin systems demonstrate excellent adhesion to a wide variety of surfaces, such as glass, wood, ceramics, masonry, leather and various plastics.		
	Notes: (1) Araldite [®] GY260 (Hunstman) or Epikote 828™ (Momentive), (2) Epikote™ 1001 (Momentive) or Araldite [®] 6100 (Hunstman), (3) Ancamine [®] K54 (Air Products)		
Product Safety	Please refer to the corresponding Safety Data Sheet.		
Storage & Handling	CRAYAMID [®] 140 should be stored indoors in the original, unopened and undamaged containe in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should b avoided. In the above mentioned storage conditions the shelf life of the resin will be 12 months from th shipping date		

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement. See MSDS for Health & Safety Considerations.

Arkema Coating Resins 420, rue d'Estienne d'Orves 92705 Colombes Cedex - France arkema.com - arkemacoatingresins.com

