

Technical Data Sheet

EPIKURE™ Curing Agent 3290

Product Description

EPIKURE™ Curing Agent 3290 is a modified aliphatic amine, light colored, low viscosity epoxy curing agent. Systems cured with EPIKURE 3290 exhibit excellent solvent resistance. Mix ratios are less critical than standard polyamines.

Application Areas/Suggested Uses

- Metal and plastic adhesives
- Small castings
- Laminates
- Electrical potting
- Automotive body patching compounds
- Tooling compounds

Benefits

- Reduced vapor pressure
- Low shrinkage
- Less critical mix ratios
- Good chemical resistance
- Low mixed viscosity

Sales Specifications

Property	Value	Unit	Test Method
Amine Value	990 - 1020	mg/g	ASTMD2896
Color	4	Gardner	ASTMD1544
Viscosity at 25°C	350 - 450	cP	ASTMD2196

Typical Properties

Property	Value	Unit	Test Method
Appearance	Clear and free of foreign particles		
Density @ 25°C	8.5	lbs/gal	ASTMD1475
Equivalent Weight Approx.	48		
Flash Point	>110	°C	ASTMD3278
Mix Ratio EPON™ Resin 828	25		

Performance Properties

EPIKURE Curing Agent 3290
<http://www.westlakeepoxy.com/en-US/product/epikure-curing-agent-3290>

Generated: May 24, 2022
 Issue Date:
 Revision: 8/1/2007 12:00:00 AM

© and ™ Licensed trademarks of Westlake Inc.

The information provided herein was believed by Westlake Inc. ("Westlake") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Westlake Epoxy are subject to Westlake Epoxy's terms and conditions of sale. **WESTLAKE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY WESTLAKE,** except that the product shall conform to Westlake's specifications. Nothing contained herein constitutes an offer for the sale of any product.

Table 1 / Properties of epoxy systems cured with EPIKURE Curing Agent 3290

Composition	Method	Units	A	B	C	D
EPON™ Resin 828		pbw	100	–	–	–
EPON Resin 813		pbw	–	100	–	–
EPON Resin 815		pbw	–	–	100	–
EPON Resin 8132		pbw	–	–	–	100
EPIKURE 3290 Curing Agent		pbw	25	25	25	23
Handling Properties @ 25°C						
Viscosity, Initial		cP	5,400	880	800	800
Pot Life, 100 gram mass		min	23	27	31	33
Cured State Properties¹						
Heat Deflection Temperature	ASTM D648	°C	98	55	59	50
Tensile Strength	ASTM D638	psi	10,740	10,010	7,945	8,838
Tensile Elongation at break		%	10.0	6.7	9.6	9.6
Flexural Strength	ASTM D790	psi	16,954	19,316	16,694	14,162
Flexural Modulus, Initial		ksi	440	570	480	420
Hardness		Shore D	88	86	84	82
Chemical Resistance²						
Water absorption		%	0.19	0.15	0.24	0.23
5% Acetic Acid		%	1.10	4.24	4.66	3.68

EPIKURE Curing Agent 3290
<http://www.westlakeepoxy.com/en-US/product/epikure-curing-agent-3290>

Generated: May 24, 2022
Issue Date:
Revision: 8/1/2007 12:00:00 AM

© and ™ Licensed trademarks of Westlake Inc.

The information provided herein was believed by Westlake Inc. ("Westlake") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Westlake Epoxy are subject to Westlake Epoxy's terms and conditions of sale. **WESTLAKE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY WESTLAKE**, except that the product shall conform to Westlake's specifications. Nothing contained herein constitutes an offer for the sale of any product.

Composition	Method	Units	A	B	C	D
5% Sodium hydroxide		%	0.17	0.12	0.27	0.20
50% Xylene/50% Isopropanol		%	-0.03	2.48	0.41	2.23

¹Determined on 1/8-inch thick test specimens cured 24 hrs at 25 °C followed by 2 hrs at 100 °C.

²Percent weight gain after immersion for 24 hrs at 25 °C.

Safety, Storage & Handling

Please refer to the MSDS for the most current Safety and Handling information.

Please refer to the Hexion web site for Shelf Life and recommended Storage information.

Exposure to these materials should be minimized and avoided, if feasible, through the observance of proper precautions, use of appropriate engineering controls and proper personal protective clothing and equipment, and adherence to proper handling procedures. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheet (MSDS) for these and all other products being used are understood by all persons who will work with them. Questions and requests for information on Hexion Inc. ("Hexion") products should be directed to your Hexion sales representative, or the nearest Hexion sales office. Information and MSDSs on non-Hexion products should be obtained from the respective manufacturer.

Packaging

Available in bulk and drum quantities.

Contact Information

For product prices, availability, or order placement, please contact customer service:

www.hexion.com/Contacts/

For literature and technical assistance, visit our website at www.hexion.com