

Technical Data Sheet

Re-issued September 2005

EPON™ Resin 8201

Product Description

EPON™ Resin 8201 is a liquid epoxy resin blend with superior resistance to pigment and filler settling; thus giving greater stability to highly-filled compounding formulations. This resin has a low level of monofunctional diluent (HELOXY™ Modifier 62) to reduce viscosity, provide better wetting, yield higher filler acceptance and improve bubble release. Because of these features, EPON Resin 8201 offers superior resistance to foaming under vacuum processing

Application Areas/Suggested Uses

- Adhesives
- Flooring
- Tooling
- Electrical casting and encapsulation
- Grouting compounds
- High solids coatings

Benefits

- Low viscosity for easy pumping and handling
- High resistance to filler settling
- Low foaming

Sales Specification

Property	Units	Value	Test Method/Standard
Weight per Epoxide	g/eq	180 – 195	ASTM D1652
Viscosity at 25°C	P	50 – 65	ASTM D445
Color	Gardner	1 max.	ASTM D1544

Typical Properties

Property	Units	Value	Test Method/Standard
Density at 25°C	lb/gal	9.7	ASTM D1475

--	--	--	--

¹Vapor pressure of pure cresyl glycidyl ether.

Safety, Storage & Handling

Please refer to the MSDS for the most current Safety and Handling information.

Exposure to these materials should be minimized and avoided, if feasible, through the observance of proper precautions, use of appropriate engineering controls and proper personal protective clothing and equipment, and adherence to proper handling procedures. **None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheet (MSDS) for these and all other products being used are understood by all persons who will work with them.** Questions and requests for information on Hexion Inc. ("Hexion") products should be directed to your Hexion sales representative, or the nearest Hexion sales office. Information and MSDSs on non-Hexion products should be obtained from the respective manufacturer.

Packaging

Available in bulk and drum quantities.

Contact Information

For product prices, availability, or order placement, please contact customer service:

www.hexion.com/Contacts/

For literature and technical assistance, visit our website at: www.hexion.com

© and ™ Licensed trademarks of Hexion Inc.

DISCLAIMER

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION,** except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.

PDS-4052- (Rev.9/3/2015 4:32:10 PM)