

PHOTOMER® 4135 Monomer, Reactive Diluent

Product Data Sheet

General Information

PHOTOMER® 4135 is a low odour, low volatility mono-functional acrylated monomer which can be polymerised in the presence of free radicals. It is typically used in UV- and EB curable applications and is particularly suited to use in coatings for optical media.

Chemical Data

Chemical Name: o-phenylphenoxyethyl acrylate

 Molecular weight
 : 268 g/mol

 CAS No.
 : 72009-86-0

 EC No.
 : 500-247-9

Specification

Appearance Visual Clean and clear liquid

Viscosity @ 25 °C Brookfield, ISO 2555 120 - 150 mPa.s

Colour (APHA) ISO 6271 ≤ 100

Acid Value ISO 660 ≤ 0.5 mg KOH/g

Moisture content Karl Fischer, ISO 4317 ≤ 0.2%

Inhibitor content Spectrophotometer 100 – 400 ppm MEHQ

Specific Gravity @ 25°C 1.130 - 1.150 g/cm³

Refractive index ISO 489 1.5700 - 1.5800

Applications

PHOTOMER® 4135 may be used, after adequate testing, in the following UV curable application areas:

- Coatings for optical media
- Coatings and inks for substrates such as paper, wood, metal and plastics.
- Adhesives
- Electronics

Issue: 25/07/2014 ©IGM Resins PDS 4135 Version:005 Page 1 of 2

Features & Benefits

PHOTOMER® 4135 exhibits a high refractive index and good impact strength.

Storage & Handling

Storage must be in a cool, shaded, well ventilated and dry area away from direct sources of heat and sunlight. Subject to appropriate storage under the usual storage and temperature conditions, our products are durable for at least 12 months.

PHOTOMER® 4135 should be handled in accordance with good industrial practice. Further information is provided in the material safety data sheet which is available on request.

Regulatory Status

TSCA (USA), EU (Europe), IECSC (China), NDSL (Canada), ECL (Korea), ENCS (Japan) and Taiwan

Packaging

PHOTOMER® 4135 is available in 200Kg drums.

Disclaimer

The information presented in this data sheet is given in good faith and is based on the material available to us at the time of writing. The information is not to be taken as a warranty or representation for which we assume legal responsibility, nor as permission or recommendation to practice any patented invention without a license. It is offered solely for consideration, investigation and verification.

Issue: 25/07/2014 ©IGM Resins PDS 4135 Version:005 Page 2 of 2