


TECHNICAL DATA SHEET SDL-552



Molecular Formula:	C14H30N2O6
Molecular Weight:	320
Appearance:	White Crystalline Powder
Hydroxy Value:	600 – 725 mg KOH/g
Water Content:	1.0% max.
Melting Point:	120 – 126° C
Color Gardner:	1 Max.

Package

25 Kgs net/fiber drum. 13 Mts/20'FCL

Uses

An excellent curing agent for polyester powder coatings.

Manufactured By

Yangzhou Sandeli Chemical Co., Ltd.