

CYCAT® 500 catalyst

September 2019



PRODUCT DESCRIPTION

CYCAT 500 catalyst is a strong acid catalyst based on dinonylnaphthalene disulfonic acid supplied in isobutanol. It is recommended to accelerate the cure between hydroxyl, carboxyl, and amide functional groups with alkylated amino crosslinking agents. CYCAT 500 is recommended for use in electrocoating applications to achieve cure in the range of 110-135°C in 15-30 minutes, or to reduce the baking time at higher baking temperatures. CYCAT 500 is also recommended for coatings applied by other application techniques, providing improved adhesion and resistance properties compared with other sulfonic acid catalysts.

BENEFITS

- Reduces energy requirements
- No decrease in electrocoat bath stability
- High electrical resistivity
- Improves resistance properties

APPLICATION AREAS

- Primers
- Electrocoat
- Coil coating finishes
- High solids systems
- Electrostatic spray systems

PHYSICAL/CERTIFIED PROPERTIES

Property	Value	Method
Acid Value (mg KOH/g)	80-90	ISO 2114
Appearance	Clear, amber liquid	ASTM E284
Color, Gardner	≤ 12	DIN EN ISO 4630-1

TYPICAL PROPERTIES (NOT CONTINUALLY MEASURED)

Property	Value	Method
Density, g/ml	~0.93	DIN EN ISO 2811-2

SOLUBILITY

CYCAT 500 catalyst is soluble in most commonly used organic solvents. Its solubility in water is limited.

CATALYST ADDITION

CYCAT 500 catalyst contains approximately 40% active acid. Recommended dosage is 1-3% on total resin solids depending upon cure schedule.

STORAGE STABILITY

CYCAT 500 catalyst has a shelf life of 365 days when stored at temperatures below 32°C.

www.allnex.com

Disclaimer: allnex Group companies ("allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform his/her own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with ®, ™ or * as well as the allnex name and logo are registered, unregistered or pending trademarks of Allnex IP s.à.r.l. or its directly or indirectly affiliated allnex Group companies.