

ADDITOL® XW 6528

TYPE

Water dilutable, modified polyester-acrylate polymer

Neutralization agent

1.5 % dimethyl ethanol amine, as salt

FORM OF DELIVERY (f.o.d.)

 35 % in water (35WA)
 (containing also 5.3 % butyl glycol)

PRODUCT DATA

Determined per batch:

 Dynamic Viscosity DIN EN ISO 3219
 dynamic viscosity [mPa.s] 2000 - 15000
 (25 1/s; 23 °C)

 pH-Value DIN ISO 976
 pH-value 7,5 - 8,5
 (10 %)

 Non-Volatile Matter DIN EN ISO 3251
 non-volatile matter [%] 34 - 36
 (1 h; 125 °C; 1 g)

 Colour / Appearance VLN 250
 colour yellowish
 appearance opaque

Not continually determined:

 Density (Liquids) DIN EN ISO 2811-2
 density [g/cm³] 1,03
 approx. (20 °C)

 Flash Point (Pensky-Martens) DIN EN ISO 2719
 flash point [°C] > 100

SPECIAL PROPERTIES AND USE

Additol XW 6528 is a water dilutable grinding medium which can be used for colour- and shading pigment pastes. It is compatible in waterborne air-drying and stoving alkyds, waterborne acrylic resins, UV- curing systems, anodic deposition dipping lacquers, PU- dispersions and plastic dispersions. Additol XW 6528 is co-crosslinking in melamine and isocyanate curing systems.

It offers excellent wetting power for both inorganic and organic pigments. The pigment pastes are compatible with a wide variety of water dilutable binder systems. Special characteristics of binder systems remain unchanged by the use of Additol XW 6528. Leveling and gloss of coatings get improved.

PROCESSING

	Kronos 2310	Paliogen- red L 4120	Printex U
Additol XW 6528	24,27	50,00	60,17
deionized water	9,76	15,80	18,53
Additol VXW 6387 (antissettling agent)	1,90		
Aerosil 200	0,25		
Additol VXW 6374 (wetting agent)		3,00	1,81
Additol VXW 4973 (defoamer)	0,61	1,20	1,44
pigment	63,21	30,00	18,05
	100,00	100,00	100,00

STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 365 days.

Synthetic resins containing water may freeze or get inhomogeneous at temperatures below 0 °C. By this the product will not suffer any damage, but the necessary regeneration requires extended heat treatment at 40 - 50 °C with continuous stirring. It is therefore recommended to ensure frostproof storage of such products.

DISTINGUISHING FEATURES

Due to the co-crosslinking capability of Additol XW 6528 in melamine and isocyanate systems final coatings show better chemical resistance and salt spray test results compared to any other type of waterborne grinding resin.

7.0/17.07.2013 (replaces all previous versions)

• Worldwide Contact Info: www.allnex.com •

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.