

ADDITOL® XW 6533

PRELIMINARY PRODUCT INFORMATION

TYPE

Cobalt-free combination drier, water-emulsifiable

DEVELOPMENT PRODUCT

This product is serving for trial purposes only. Deviations which might occur during transfer into manufacturing in a commercial scale are possible and do not constitute any material defect.

Metal content

approx. 1,2 % Manganese
approx. 12 % Zirconium

SPECIAL PROPERTIES

The cobalt-free combination drier Additol XW 6533 produces in waterborne alkyd resin paints a good set-drying combined with an even through-drying.

Additol XW 6533 contains a balanced metal combination which is necessary for an optimum oxidative drying.

TENTATIVE PRODUCT DATA

Determined per batch:

Colour / Appearance VLN 250
colour brown

Dynamic Viscosity DIN EN ISO 3219
dynamic viscosity [mPa.s] 100 - 600
(25 1/s; 23 °C)

Non-Volatile Matter DIN EN ISO 3251
non-volatile matter [%] 59 - 63
(1 h; 125 °C; 1 g)

Not continually determined:

Density (Liquids) DIN EN ISO 2811-2
density [g/cm³] 1,12
approx.
(20 °C)

Flash Point (Pensky-Martens) DIN EN ISO 2719
flash point [°C] 65
approx.

SUGGESTED USES

Additol XW 6533 may be added as siccative to all waterborne oxidatively drying alkyd resin paints.

PROCESSING

Additol XW 6533 may be added undiluted to the resin in form of delivery. In critical systems we recommend to disperse the combination drier with the pigments and fillers.

Recommended quantity to be added: 4 - 6 %, calculated on solid resin.

STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 730 days.

When stored at temperatures below 20 °C Additol XW 6533 tends to slight crystallization, which is reversible by heating for 24 hours to 40 °C.

REMARK:

Data contained in this publication are based on careful investigations (and are intended for information only). Due to scale up of this product there is not yet sufficient experience concerning serial production. We can therefore not exclude, that based on future knowledge product data and other indicated properties in upcoming Technical Data Sheets will be subject to change. We reserve the right to leave the product name unchanged, even if product data or other indicated properties will vary from the present product info. Regardless of the data contained in this publication any user is obliged to carry out tests under his own responsibility as to the suitability of the product for a particular use and to investigate the possible violation of industrial property rights of third parties. Information is therefore not binding and cannot be construed as guaranteeing specific properties of products. We apply our General Sales Conditions.

6.0/30.03.2017 (replaces 5.0/17.09.2013)

• Worldwide Contact Info: www.allnex.com •

Disclaimer: allnex Group companies ("allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.

© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.