

TECHNICAL DATA SHEET

CRAYVALLAC® FLOW-450

High performance polyacrylate based flow and leveling agent for the control of surface properties
Polyacrylate

TYPICAL CHARACTERISTICS

Nature	Polyacrylate
Appearance	Clear liquid
Solid Content (%)	52
Active Content (%)	52
Brookfield viscosity (mPa.s)	100-500
Specific gravity	0.95
Solvent	Butyl Acetate

DESCRIPTION

CRAYVALLAC® FLOW-450 is used to improve flow and eliminate air entrapment, orange peel, pinholes, craters and other surface defects. It is an additive based on polyacrylate technology to provide excellent ageing resistance to coatings. CRAYVALLAC® FLOW-450 is also used as an adhesion promoter additive with excellent performance. CRAYVALLAC® FLOW-450 can furthermore successfully substitute classical defoamers within a formulation, demonstrating combined performance in terms of leveling and defoaming. CRAYVALLAC® FLOW-450 is easily incorporated into formulations due to its wide compatibility in most solvents. It is recommended to incorporate CRAYVALLAC® FLOW-450 in the mill-base in order to get maximum efficiency in terms of air release properties.

STANDARD PACKAGING

Other packaging may be available upon request

- 190 Kg Drum

HANDLING & STORAGE

It should be stored in the original containers in a dry place at temperatures between 5°C (41°F) and 30°C (86°F). Avoid exposure to direct sunlight or frost.
In these conditions, this product should be used within 24 months from production.

HEALTH AND ENVIRONMENTAL DATA

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

MARKETS

Coatings & Inks

- Graphic Arts
- Industrial Coating
- Textile & Leather Coating
- Inks

KEY BENEFITS

FORMULATION

- Post addition
- Ready to use
- Easy handling



APPLICATION

- Air release



FILM PROPERTIES

- Gloss
- Levelling
- Defects reduction



SAFER SOLUTIONS

- APEO Free*
- Heavy Metal Free*

* Not intentionally added but not specifically measured (not part of product specification)

Headquarter: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80