

TECHNICAL DATA SHEET

CRAYVALLAC® WN-1150

Modified polyethylene matting agent for powder coatings

Micronised wax

TYPICAL CHARACTERISTICS

Nature	Special wax
Appearance	Off-white micronized powder
Active Content (%)	100
Melting Point (°C)	112

DESCRIPTION

CRAYVALLAC® WN-1150 is used to control gloss between 30 – 60% for epoxy/polyester hybrid, HAA and TGIC based polyester powder coatings. No effect on weather ability or physical properties.

RECOMMENDED ADDITION LEVEL

1.0 - 6.0%

STANDARD PACKAGING

Other packaging may be available upon request

- 15 Kg Bag

HANDLING & STORAGE

It should be stored in the original containers in a dry place at temperatures between 5°C (41°F) and 30°C (86°F). Avoid exposure to direct sunlight or frost. In these conditions, this product should be used within 48 months from production.

PROCESSING INSTRUCTIONS

Simple dispersion and blending with other powder components.

HEALTH AND ENVIRONMENTAL DATA

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

MARKETS

- Coatings & Inks
- Graphic Arts
 - Industrial Coating

KEY BENEFITS

FORMULATION

- Ready to use
- Easy handling



FILM PROPERTIES

- Matting effect



SAFER SOLUTIONS

- APEO Free*
- Heavy Metal Free*
- Solvent Free*

* Not intentionally added but not specifically measured (not part of product specification)

Headquarter: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80