

RHEOTECH™ 3800

Acrylic associative thickener for water-based systems

HASE Acrylic Thickener

TYPICAL CHARACTERISTICS

Nature	Aqueous dispersion of an acrylic copolymer
Appearance	Low viscous white milky liquid
Solid Content (%)	30
Active Content (%)	30
pH	3
Specific gravity	1.06
Solvent	Water

DESCRIPTION

Rheotech™ 3800 is an acrylic associative thickener for water-based systems (also called HASE). It is designed to improve both the rheology and the color acceptance of water-based formulations. Its outstanding effectiveness at medium shear rates allows to control very easily the perceived quality of paints during handling and to facilitate coating by roll or by brush, especially for finishing touches.

RECOMMENDED ADDITION LEVEL

Rheotech™ 3800 can be used alone in formulation showing high PVC, e.g. matt paints, fillers and low cost formulations, at concentration between 0.1 and 0.6% (dry on total formulation weight) typically. It can also be used in combination with other rheology modifiers such as cellulosic ethers, Newtonian acrylic thickeners and polyurethane thickeners for an easy rheology adjustment of all kinds of water based formulations, e.g. one coat matt paints or silk paints (concentrations to use: 0.05 to 0.4%).

STANDARD PACKAGING

Other packaging may be available upon request

- 1000L IBC
- 200L Drum
- Bulk

HANDLING & STORAGE

It can be irreversibly altered by frost. It should be protected from the effects of weathering and stored between 5 and 40°C and protected from direct sun exposure.

Once opened, packaging should be resealed immediately after use.

Film-forming product, surface may dry in contact with air.

A slight sedimentation can be visible at the bottom of drums or totes. This phenomenon is normal and has no impact on the use and level of performance as long as the solids content of the product meets the specification. If necessary, filter the product prior to its use.

In these conditions, this product should be used within 6 months from delivery.

PROCESSING INSTRUCTIONS

Rheotech™ 3800 should be added under stirring at the end of formulation, after the binder incorporation. The thickening effect is achieved once the pH of the formulation is brought to 8.5 to 9 using an alkali solution (sodium hydroxide, ammonium hydroxide, amines).

HEALTH AND ENVIRONMENTAL DATA

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

MARKET

Coatings & Inks

- Architectural Coating
- Graphic Arts
- Industrial Coating
- Textile & Leather Coating

KEY BENEFITS

FORMULATION

- **Color acceptance**
- **Cost in use**
- **Compatibility**



STORAGE

- **In-can appearance**
- **Syneresis resistance**
- **Antisettling**
- **Viscosity stability**



APPLICATION

- **Tinting resistance**
- **Brushability**
- **Dilution resistance**



FILM PROPERTIES

- **Rub out**
- **Hiding power/Opacity**
- **Stain resistance**



- **APEO free** **Yes**
- **Bacteria resistance** **Yes**
- **Heavy metal free** **Yes**
- **Solvent-free** **Yes**

THICKENING MECHANISM

Non Associative

Associative

Self Association

VISCOSITY CONTRIBUTION

Low Shear contribution

Mid Shear contribution

High Shear contribution

PVC

PVC High

PVC Mid

RHEOTECH™ 3800

Acrylic associative thickener for water-based systems

HASE Acrylic Thickener

HEALTH AND ENVIRONMENTAL DATA

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.