

TECHNICAL DATA SHEET

RHEOTECH™ 3900

Acrylic associative thickener for water-based systems

HASE Acrylic Thickener



26% Bio Carbon Content (only for EMEA supply)
-20% Carbon Footprint Reduction (only for EMEA supply)

TYPICAL CHARACTERISTICS

Nature	Aqueous dispersion of an acrylic copolymer
Appearance	Low viscous white milky liquid
Solid Content (%)	30
Active Content (%)	30
pH	3
Specific gravity	1.06
Solvent	Water
Total Bio content (%)	26

DESCRIPTION

Rheotech™ 3900 is an associative acrylic thickener designed to improve both the rheology and the color acceptance of water based formulations. Its outstanding effectiveness at medium shear rates allows to control very easily the perceived quality of paints during handling and to facilitate coating by roll or by bush, especially for finishing touches. Rheotech™ 3900 ensures safe additions of colorants in water based formulations, limiting viscosity changes and rub-out issues. Rheotech™ 3900 can be used in every kind of alkaline water based formulation and particularly in solvent and Alkyl Phenol Ethoxylate (APE) free formulations.

RECOMMENDED ADDITION LEVEL

Rheotech™ 3900 can be used alone in formulation showing high PVC, e.g. matt paints, fillers and low cost formulations, at concentration between 0.1 and 0.6% (dry on total formulation weight) typically. Rheotech™ 3900 can also be used in combination with other rheology modifiers such as cellulosic ethers, Newtonian acrylic thickeners and polyurethane thickeners for an easy rheology adjustment of all kinds of water based formulations, e.g. one coat matt paints or silk paints (concentrations to use: 0.05 to 0.4%).

STANDARD PACKAGING

Other packaging may be available upon request

- 1000L IBC
- 200L Drum
- Bulk

MARKETS

Coatings & Inks

- Architectural Coating
- Graphic Arts
- Industrial Coating
- Textile & Leather Coating

KEY BENEFITS

FORMULATION

- Color acceptance
- Compatibility
- Cost in use



STORAGE

- Syneresis resistance
- In-can appearance
- Viscosity stability
- Antisettling



APPLICATION

- Brushability
- Rollability
- Sprayability



FILM PROPERTIES

- Rub out
- Stain resistance
- Hiding power/Opacity



SAFER SOLUTIONS

- APEO Free*
- Heavy Metal Free*
- LiCl Free*
- MIT Free*
- Solvent Free*

* Not intentionally added but not specifically measured (not part of product specification)

- Total Bio content (%) 26

RHEOTECH™ 3900

HANDLING & STORAGE

It can be irreversibly altered by frost. It should be protected from the effects of weathering and stored between 5 and 40°C and protected from direct sun exposure. Once opened, packaging should be resealed immediately after use. Film-forming product, surface may dry in contact with air. A slight sedimentation can be visible at the bottom of drums or totes. This phenomenon is normal and has no impact on the use and level of performance as long as the solids content of the product meets the specification. If necessary, filter the product prior to its use. In these conditions, this product should be used within 6 months from delivery.

PROCESSING INSTRUCTIONS

Rheotech™ 3900 can be added under stirring at the end of formulation, after the binder incorporation, or alternatively into the millbase like cellulosic ether thickeners. The thickening effect is achieved once the pH of the formulation is brought to 8.5 to 9 using an alkali solution (sodium hydroxide, ammonium hydroxide, amines).

HEALTH AND ENVIRONMENTAL DATA

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

THICKENING MECHANISM

Non Associative
Self Association
Associative



VISCOSITY CONTRIBUTION

Low Shear contribution
Mid Shear contribution
High Shear contribution



PVC

PVC Low
PVC Mid
PVC High



Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80