

TECHNICAL DATA SHEET

SYNAQUA 9544 BA 75*(Formerly CHEMPOL® 310-1744)**Thermoset acrylic***PRODUCT APPLICATION DETAILS**

SYNAQUA 9544 BA 75 is a carboxyl functional, thermosetting water reducible acrylic with excellent flexibility, solvent resistance, gloss, and impact resistance.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	75%	-
Viscosity	Z5-Z5Gardner Holdt	-
Color	1Gardner	-
Acid value	101mg KOH/g	-

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	n-Butanol	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS**Coatings & Inks**

- Industrial Coating
 - General Industry

SYNAQUA 9544 BA 75

(Formerly CHEMPOL® 310-1744)

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNAQUA 9544 BA 75 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

Arkema Coating Resins
410 Gregson Dr.
Cary, NC 27511 – USA
T +1 919 469 6700

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

ARKEMA