

TECHNICAL DATA SHEET

Synolac® 8045 MK 75 (Formely CHEMPOL® 809-3145)

PRODUCT APPLICATION DETAILS

Synolac® 8045 MK 75 is a high solids chain-stopped soya/DCO short oil alkyd with fast surface dry times, superior gloss retention, and excellent early water spot resistance, for use in 2K urethane metal coatings. Synolac® 8045 MK 75 is the HAPs-free version of CHEMPOL® 809-3132.

SALES SPECIFICATIONS

| | CHARACTERISTICS | METHODS |
|--------------------------------|--------------------|---------|
| Solid content | 75 % | - |
| Viscosity | Y-Z1 Gardner Holdt | - |
| Reduced viscosity (60% in MAK) | D-F | - |
| Color | 8 Gardner | - |
| Acid value | 12 mg KOH/g | - |

OTHER CHARACTERISTICS¹

| | CHARACTERISTICS | METHODS |
|----------------------------|-----------------|---------|
| Solvent | MAK | - |
| Density | 8.7 lbs/gal | - |
| Hydroxyl content | 1.9 % | - |
| Hydroxyl equivalent weight | 876 | - |
| Hydroxyl number | 64 | - |

^{&#}x27;The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- · Industrial Coating
 - Automotive OEM
 - General Industry

PERFORMANCE BENEFITS

- Fast surface dry
- Good early water spot resistance
- Excellent Florida gloss retention
- May be forced dried
- Excellent resin for alkyd 2K urethane coatings



FORMULATION GUIDELINES

RECOMMENDATIONS OF USE

Agricultural and Heavy Equipment coatings Transportation finishes General Industrial metal **Machinery Enamels**

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

Synolac® 8045 MK 75 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

> **Arkema Coating Resins** 410 Gregson Dr. Cary, NC 27511 – USA T +1 919 469 6700

Headquarters: Arkema France 51, Esplanade du Général de Gaulle 92800 Puteaux – France T +33 (0)1 49 00 80 80

Coating Resins - 2025-11-10 - Page: 2 / 2