

TECHNICAL DATA SHEET

Synolac® 8084 X 90 (Formerly CHEMPOL® 803-4084)  
Short Oil Alkyd

PRODUCT APPLICATION DETAILS

Synolac® 8084 X 90 is a high solids short oil TOFA baking alkyd with high hardness and low temperature cure, for use in metal coatings.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	90+ %	-
Viscosity	Z4-Z6 Gardner Holdt	-
Reduced viscosity (70% in n-Butyl Acetate)	D-G Gardner Holdt	-
Color	10 Gardner	-
Acid value	15 mg KOH/g	-

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Xylene	-
Density	9.23 lbs/gal	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
  - General Industry

PERFORMANCE BENEFITS

- Rapid Viscosity Reduction
- High Hardness
- Low Temperature Cure
- Good Compatibility

# SYNOLAC<sup>®</sup> 8084 X 90

(Formerly CHEMPOL<sup>®</sup> 803-4084)

## FORMULATION GUIDELINES

### RECOMMENDATIONS OF USE

Metal Furniture Coatings  
Structural steel coatings  
General Industrial Metal

## PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

## STORAGE AND HANDLING

Synolac<sup>®</sup> 8084 X 90 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

**Arkema Coating Resins**  
410 Gregson Dr.  
Cary, NC 27511 – USA  
T +1 919 469 6700

**Headquarters: Arkema France**  
51, Esplanade du Général de Gaulle  
92800 Puteaux – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.  
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790