

TECHNICAL DATA SHEET

Synolac® 8105 S 50 (Formely CHEMPOL 802-1005)

Medium oil alkyd

PRODUCT APPLICATION DETAILS

 $\mbox{Synolac}^{\circ}$ 8105 S 50 is a medium oil soya alkyd with excellent gloss, dry time, workability, and color retention.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	50 %	-
Viscosity	Z-Z2 Gardner Holdt	-
Reduced viscosity (40% in Mineral Spirits)	J-M Gardner Holdt	-
Color	6 Gardner	-
Acid value	10 mg KOH/g	-

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Mineral spirits	-
Density	7.6 lbs/gal	-
Hydroxyl content	1.6 %	-
Hydroxyl number	54	-

¹ The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
 - General Industry
 - Wood Furniture

PERFORMANCE BENEFITS

- Excellent Gloss, Drying, Workability, and Color Retention
- Recommended Dryers on Vehicle Solids; 0.05% Cobalt, 0.50% Zirconium



PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

Synolac® 8105 S 50 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

> **Arkema Coating Resins** 410 Gregson Dr. Cary, NC 27511 – USA T +1 919 469 6700

Headquarters: Arkema France 51, Esplanade du Général de Gaulle 92800 Puteaux – France T +33 (0)1 49 00 80 80 Coating Resins - 2025-11-10 - Page: 2 / 2