

TECHNICAL DATA SHEET

ENCOR[®] DL 313

Styrene butadiene Emulsion

PRODUCT APPLICATION DETAILS

Binder for primer sealers that require moisture vapor barrier properties, alkali resistance and adhesion to galvanized metals.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	49.0 %	-
pH	8.5	-
Viscosity (#3 spindle @ 60 rpm. Brookfield LV)	300 cP	-

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Minimum film formation temperature	0 °C	-
Glass transition temperature (DSC)	-1 °C	-
Density	8.6	-
Average particle size	100 nm	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Architectural Coating
 - Exterior Wall
 - Primers
 - Specialty Coatings
- Flooring
 - Floor Polish & Floor Coatings

ENCOR® DL 313

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

ENCOR® DL 313 - When storing and handling follow procedures recommended for polymer dispersions. Use corrosion resistant storage tanks and piping. Air-operated diaphragm pumps are preferred. Avoid temperature extremes. Do not freeze. Store between 40 to 90 °F (4 -32 °C). Packaged material should be stored indoors in a dry place in the original unopened and undamaged container. Exposure to direct sunlight should be avoided. The product is protected to prevent microbial deterioration during normal storage conditions; however, care should be taken to avoid accidental contamination during subsequent handling and processing. Bulk storage and handling practices are described in the Arkema Latex Storage and Handling Guide. For a copy of this guide contact Arkema.

Arkema Coating Resins
410 Gregson Dr.
Cary, NC 27511 – USA
T +1 919 469 6700

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790