

TECHNICAL DATA SHEET

SNAP[®] 720

Acrylic Emulsion

PRODUCT APPLICATION DETAILS

Binder that offers outstanding block resistance in low or zero VOC high-gloss coatings, and is an excellent choice for low odor systems.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	49.0 %	-
pH	7.0	-
Viscosity (#3 spindle @ 60 rpm. Brookfield LV)	<500 cP	-

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Minimum film formation temperature	<5 °C	-
Density	8.9	-
Average particle size	80 nm	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Architectural Coating
 - Exterior Wall
 - Interior Wall
 - Specialty Coatings
 - Stains
 - Trim
- Flooring
 - Floor Polish & Floor Coatings

SNAP® 720

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SNAP® 720 should be stored indoors in the original, unopened and undamaged container, in a dry place at storage temperatures between 5°C and 30°C. Exposure to direct sunlight should be avoided. The product is protected to prevent any microbial deterioration during normal conditions of storage but care should be taken to avoid accidental contamination during subsequent handling and processing. In the above mentioned storage conditions the shelf life of the resin will be from the shipping date.

Arkema Coating Resins
410 Gregson Dr.
Cary, NC 27511 – USA
T +1 919 469 6700

Headquarter: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790