
S-1403-L

Water Based Polyurethane Dispersion

Product Description

- APEO/NMP free urethane dispersion
- Excellent chemical resistance
- Fast drying dispersion for formulated coatings top coats

Product Properties

Solids (%): 34-36
VOC (g/L): 111- 113
Gloss @ 60°: 80-100

Film Properties

Tensile (D-882, psi): 6,200
Elongation (D-882, %): 420
Pencil Hardness (D-3363): 2B

Substrate Cross-Cut Adhesion

Cold Roll Steel-unpolished: 5B
Aluminum-untreated: 5B
Brass-untreated: 5B
HDPE-untreated: 0B

ABS-untreated: 0B
Polycarbonate-untreated: 0B
Nylon-untreated: 0B

Chemical Resistance

(5=no damage, films dried for 15 minutes at 80°C, then equalized at room temp. for 7 days, tested using ASTM D-1308)

Water: 5
Acetic Acid: 5
Ammonia: 5
Methyl Ethyl Ketone: 5
2-Propanol: 5
Gasoline: 5

Synthetic Natural Polymers

Durham, NC Phone: 919-598-0400
Revised July 21, 2023

