

---

---

# S-1407-L

## Water Based Polyurethane Dispersion

---

---

### **Product Description**

- APEO free urethane dispersion containing NMP
- Excellent abrasion resistance
- Hard, chemical resistant film for formulated coatings top coats

### **Product Properties**

Solids (%):	34-36
VOC (g/L):	106.1
Gloss (%) @ 60°:	85
Charge:	Anionic

### **Film Properties**

Tensile (D-882, psi):	5,000
Elongation (D-882, %):	225
Pencil Hardness (D-3363):	HB
Dry Time (D-5895, min.):	195

### **Substrate Cross-Cut Adhesion**

Cold Roll Steel-unpolished: 5B  
Aluminum-untreated: 5B  
Brass-untreated: 5B  
HDPE-untreated: 0B

ABS-untreated: 2B  
Polycarbonate-untreated: 0B  
Nylon-untreated: 0B

### **Chemical Resistance**

(5 = no damage. Films dried for 15 minutes at 80°C, then equalized at room temp. for 7 days. Tested using ASTM D-1308)

Water:	5
Acetic Acid:	5
Ammonia:	5
Methyl Ethyl Ketone:	5
2-Propanol:	4
Gasoline:	5

Synthetic Natural Polymers

Durham, NC Phone: 919-598-0400  
Revised May 16, 2016

