
S-1434-L

Water Based Polyurethane Dispersion

Product Description

- APEO/solvent free urethane dispersion
- Excellent flexibility
- Soft feel
- Self-crosslinking dispersion for formulated inks and coatings

Product Properties

Solids (%):	34-36
VOC (g/L):	13-14
Gloss (%) @ 60°:	70-100

Film Properties

Tensile (D-882, psi):	4,510
Elongation (D-882, %):	919
Pencil Hardness (D-3363):	4H

Substrate Cross-Cut Adhesion

Cold Roll Steel-unpolished: 5B
Aluminum-untreated: 5B
Nylon-untreated: 5B

ABS-untreated: 5B
Polycarbonate-untreated: 0B
HDPE-untreated: 0B

Chemical Resistance

(5 = no damage. Films dried for 15 minutes at 80°C, then equalized at room temp. for 7 days. Tested using ASTM D-1308)

Water:	5
Acetic Acid:	5
Ammonia:	5
Methyl Ethyl Ketone:	1
2-Propanol:	1
Gasoline:	5

Synthetic Natural Polymers

Durham, NC Phone: 919-598-0400
Revised July 21, 2023

