
S-1455-L

Water Based Polyurethane Dispersion

Product Description

- APEO/NMP free urethane dispersion
- Excellent adhesion.
- Flexible, glossy film for industrial coatings

Product Properties

Solids (%):	31-33
VOC (g/L):	101-102
Gloss (%) @ 60°:	80-100

Film Properties

Tensile (D-882, psi):	3,000
Elongation (D-882, %):	400
Pencil Hardness (D-3363):	4B

Substrate Cross-Cut Adhesion

Cold Roll Steel-unpolished: 5B
Aluminum-untreated: 5B
Brass-untreated: 5B
HDPE-untreated: 0B

ABS-untreated: 5B
Polycarbonate-untreated: 5B
Nylon-untreated: 5B

Chemical Resistance

(5 = no damage. Films dried for 15 minutes at 80°C, then equalized at room temp. for 7 days. Tested using ASTM D-1308)

Water:	5
Acetic Acid:	4
Ammonia:	1
Methyl Ethyl Ketone:	1
2-Propanol:	1
Gasoline:	5

Synthetic Natural Polymers

Durham, NC Phone: 919-598-0400

Revised July 21, 2023

