



# Technical Data Sheet

## Coatings

SYLYSIA is a highly efficient matting agent producing uniform films while reducing gloss. The 300 series, characterized by high oil absorption and low bulk density, has been widely employed as a matting agent for all types of resin paints and water-base paints. The matting characteristics are controlled directly by the amount of SYLYSIA introduced where settling is of least importance.

## Anti-Blocking

SYLYSIA is used to control blocking during the manufacturing of plastic film and sheers, as well as ink transfer in high-speed printing. SYLYSIA boasts greater anti-blocking performance at lower loading due to our accurate and consistent particle size distribution and high pore volume.

## Adhesion & Thickening

SYLYSIA is used in thickening adhesive applications of resin, rubber, sealing components and many others, acting to increase adhesion strength and durability, as well as stabilizing viscosity for longer shelf life. The 300 series SYLYSIA is effective in preventing stickiness and separation and stability regardless of environmental changes.

## Paper

SYLYSIA has proven to improve overall inkjet performance, as well as photographic printing onto diazo-sensitized paper, second traced paper, and photographic paper. SYLYSIA is also applicable for color-coated paper matting and as anti-block in various kinds of paper.

## Pharma/Personal Care

SYLYSIA has been widely used as a powdering agent or carrier for liquid medicines, fragrances, oils, and many others. Improves free flow ability in applications where moisture is not beneficial to production processes.

# SYLYSIA® 310P

SYLYSIA® (SY) is synthetically produced, amorphous and micronized silica gel characterized by high porosity and chemical purity. Fuji Silysia Chemical's SY310P is produced at our Greenville, NC facility. Fuji Silysia is dedicated to producing the highest quality micronized silica through advanced milling technologies and continuous product refinement.

Typical Physical Properties	SY310P
Whiteness (%)	96 min
Pore Volume (mL/g)	1.60
BET Surface Area (m <sup>2</sup> /g)	300
pH (at 5% slurry)	7.5
Total Volatile (%)	5.0
Oil Absorption (mL/100g)	310
Loose Bulk Density (mL/5g)	110
Average Particle Size (µm)*	2.7
Surface Treatment	None

\*SALD 2300 Shimadzu Laser Method

### Packaging Information:

8kg (17.6lb) Kraft bag with poly liner  
24 bags/pallet (192kg/423lb)

### Appearance:

White, dry powder

### Safety:

Amorphous, non-crystalline silica.  
See SDS for additional information.

### Manufacturing location:

Fuji Silysia Chemical USA LTD  
1215 Sugg Parkway  
Greenville, NC 27834  
(252) 413-0003

### Sales Office:

Fuji Silysia Chemical LTD  
1014 High House Road, Suite 200  
Cary, NC 27513  
(919) 650-1155

[www.fujisilysia.com](http://www.fujisilysia.com)

[info@fujisilysia.com](mailto:info@fujisilysia.com)

The information contained herein is believed to be accurate and reliable, but FUJI SILYSIA MAKES NO WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY OTHER EXPRESSED OR IMPLIED WARRANTY. The information herein relates only to the specific product described and not to such product in combination with any other product. Proving information as herein contained is not to be regarded by implying or otherwise conveying any rights or permission for use which would violate any patent rights, proprietary rights or violate any law, safety code, or insurance regulation.